



中国认可  
国际互认  
检测  
TESTING  
CNAS L1978



# 检测报告

## TEST REPORT



报告编号:  
REPORT NO.: 24202000116

样品名称:  
NAME OF SAMPLE: 钢管

委托单位:  
APPLICANT: 佛山市顺德区金永轩钢铁贸易有限公司

报告日期:  
DATE OF REPORT: 2020年05月07日



佛山海关综合技术中心

Comprehensive Technology Center of Foshan Customs



# 佛山海关综合技术中心

## Comprehensive Technology Center of

## Foshan Customs

地址: 中国广东省佛山市禅城区魁奇一路澜石(国际)金属交易中心十八座二层  
Add: 2/F, Building 18, Kuiqi 1st Road, Lanshi International Metals Exchange Centre,  
Chancheng District, Foshan City, Guangdong Prov., China  
Tel: +86-0757-83827981 Postcode: 528041  
Fax: +86-0757-83960353 E-mail: fsjszx@fs.gdciq.gov.cn

编号: 24202000116

日期: 2020年05月07日

第1页 共2页

### 检测报告

委托人: 佛山市顺德区金永轩钢铁贸易有限公司

#### 由委托人提供的样品信息

品名: 钢管

样品标记: N/M


送样数量: -1-条

收样日期: 2020-04-22

验讫日期: 2020-05-07

检测结果: 详见下一页

样品照片:



\* \* \* \* \*

(接 下 页)

授权签字人:

曹怀燕

声明: 1) 本实验室经中国合格评定国家认可委员会(CNAS)认可; 2) 我们已尽所知所能实施上述检验, 不能因签发本报告而免除有关各方根据合同和法律所承担的责任和义务; 3) 未经本实验室书面许可, 不得部分复制本报告; 4) 一般情况下, 检验结果仅对申请人所送样品负责。  
Note: 1) This laboratory is accredited by the China National Accreditation Service for Conformity Assessment (CNAS) for specific tests as listed in the CNAS Directory of Accredited Laboratories. 2) All inspections are carried out conscientiously to the best of our knowledge and ability. 3) This report shall not be reproduced, except in full, without the prior written approval from the issuing laboratory. 4) Ordinarily, test results only for the samples submitted by the applicant unless otherwise stated.



# 佛山海关综合技术中心

## Comprehensive Technology Center of

## Foshan Customs

地址: 中国广东省佛山市禅城区魁奇一路澜石(国际)金属交易中心十八座二层  
 Add: 2/F, Building 18, Kuiqi 1st Road, Lanshi International Metals Exchange Centre,  
 Chancheng District, Foshan City, Guangdong Prov., China  
 Tel: +86-0757-83827981 Postcode: 528041  
 Fax: +86-0757-83960353 E-mail: fsjszx@fs.gdcic.gov.cn

编号: 24202000116

日期: 2020年05月07日

第2页 共2页

### 检测报告

检测结果:

检测项目		检测方法	检测结果	单位
化学成分	碳 C	GB/T 11170-2008	0.07	%
	硅 Si		0.10	%
	锰 Mn		0.31	%
	磷 P		0.017	%
	硫 S		0.020	%
力学性能	屈服强度 (R <sub>p0.2</sub> )	GB/T 228.1-2010	294	MPa
	抗拉强度 (R <sub>m</sub> )		354	MPa
	断后伸长率 (A <sub>50</sub> )		36.5	%

\* \* \* \* \*

(报告结束)

声明: 1) 本实验室经中国合格评定国家认可委员会(CNAS)认可; 2) 我们已尽所知所能实施上述检验, 不能因签发本报告而免除有关各方根据合同和法律所承担的责任和义务; 3) 未经本实验室书面许可, 不得部分复制本报告; 4) 一般情况下, 检验结果仅对申请人所送样品负责。

Note: 1) This laboratory is accredited by the China National Accreditation Service for Conformity Assessment (CNAS) for specific tests as listed in the CNAS Directory of Accredited Laboratories. 2) All inspections are carried out conscientiously to the best of our knowledge and ability. 3) This report shall not be reproduced, except in full, without the prior written approval from the issuing laboratory. 4) Ordinarily, test results only for the samples submitted by the applicant unless otherwise stated.